



# LEYCO<sup>®</sup>-DICHT 2

## HIGHLY ELASTIC, FIBRE REINFORCED SEALANT



- Flexible, strengthened, general-purpose sealing compound
- For tears and holes within the entire building
- Is simple to handle, applied without primers, allows materials to breath
- Does not effect bitumen
- Is highly elastic

LEYCO®-DICHT 2 clings to all backgrounds within the entire range of building materials e.g.: Roofing felt, schweissbahnen, bitumen, fibre reinforces concrete, aluminium, zinc, lead, copper, sheet metal, roof stones, roofing tile, slate, wood, concrete, glass, tiles, marble, polycarbonate, acrylic glass, pond foil.

LEYCO®-DICHT 2 is suitable outstanding for sealing on: Flat roofs, rooflights, fire-place connections, chimney heads, domes etc. and for connecting joints of bath, terraces etc., for brick-work under the tiles.

## LEYCO®-DICHT 2

Product-No. 20.034

### HIGHLY ELASTIC, FIBRE REINFORCED SEALANT

#### BENEFITS

- flexible, strengthened, general-purpose sealing compound
- for tears and holes within the entire building
- is simple to handle, applied without primers, allows materials to breath
- can deal with moisture
- quickly seals and protectd against rain, frost and UV
- does not effect bitumen
- is highly elastic and allows for building movement
- tears and holes up to 5 mm can be durably sealed by simply laying on LEYCO®-DICHT 2
- by special Thixotropierungssystem slide LEYCO®-DICHT 2 also in thicker stratum strength, and/or at senkrechten surfaces not off

#### TECHNICAL DATA

Chemical basis:	modified acrylate resins
Zusatzstoffe:	Synthetikfasern
Colour:	grey
Ignition temperature:	over +240°C
Consistency:	pastily
Density:	approx. 0,94 - 1,00 with +20°C
Drying process:	1-2 mm per day
Work temp:	-5°C to +35°C
Hardening by precipitation:	air-drying
Storage:	in closed container at least 2 years
Overlineable:	After drying with acryl lacquers
Transport:	GGVS, Kl. 3, number 5c
Stability:	after hardening by precipitation against water, frost, UV radiation, to a large extent approximately mineral oils
Oekodaten:	Wasssergefaehrdungskl. = 1 (self classification)
Environmental protection:	Drums for recycling must becompletely empty, do not allow waste to reach the water course.

#### APPLICATION

Background must free of fat, dirt, grit and Moss. LEYCO®-DICHT 2 is ready for use and is not diluted. Apply with a broad brush or putty trowel. In extreme cases place on two layers. The product will be at full strength after 8 days.

Clean Tools with a cellulose nitrate solution.

#### PRECAUTION

Warning category VbF/A2 "inflammable".

Keep in a cool dry place in sealed containers. Keep away from sources of ignition. Use in ventilated areas. Keep away from children.

#### REMARK

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied. LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 09.01.04

