

# BETONAC<sup>®</sup>-DM 2

## WATER REPELLENT ADMIXTURE FOR CONCRETE AND MORTAR

### Product Description

**BETONAC-DM 2** is a balanced blend of stearate water repellants and other chemicals which, when used as an admixture, forms an internal barrier against water penetration. **BETONAC-DM 2** also increases the plasticity of mortar, reduces water absorption and thereby guards against freeze-thaw damage.

It is available in a liquid formula which contains substances for additional densification of the mortar or concrete. **BETONAC-DM 2** will not increase the air content of mortar or concrete.

### Features and Primary Applications

**BETONAC-DM 2** reduces water penetration in mortar and concrete under hydrostatic pressure. It is applied in building roof, basement, tunnel, roadway, drain tank and pumping station where water penetration resistance is required.

**BETONAC-DM 2** improves concrete compactness, anti-crack and anti-seepage performance. As a result, it compensates concrete shrinkage and saves cement consumption. The anti-seepage rate can reach up to P25.

**BETONAC-DM 2** does not reduce concrete compressive strength. It has no pollution to water and no corrosion to steel.

**BETONAC-DM 2** can be used for the interior water repellent, instead of exterior surface treatment. So that it provides continuous protection.

**BETONAC-DM 2** achieves perfect water repellent effect when combined with water reducing and air entraining admixtures. Air-entraining agent provides stable microscopic air void system with proper bubble size and spacing, which can reduce permeability. While, water reducing agent can reduce consumption, improve concrete workability, and increases concrete compactness.

- Mass concrete
- Foundation walls
- Floors
- Cement stucco
- Mortar for setting masonry

### Advantages

Reduces moisture absorption as much as 60%

- Reduces capillary action
- Reduces vapor transmission through walls and slabs
- Provides greater workability
- Does not affect bond strength of mortar

### LEYCOCHEM-IRAQ Baghdad

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151

Email: sales.leycochem.iraq@leyde.com

Email: admin.leycochem.iraq@leyde.com

[www.leyde.com](http://www.leyde.com)

### LeycoChem LEYDE GmbH Germany

Industriestrasse 155

P.O. Box 501627

D-50999 Köln/Cologne

Tel.:+49(0)2236-96600-0

Fax:+49(0)2236-96600-10

Email: leycochem@leyde.com

**Product Data Sheet**

Product No: 01.010

**Technical Data**

**Appearance/Colour**

BETONAC-DM 2 liquid has an white color

| Test Results                       | Absorption Ratio | Relative Absorption | Concrete Absorption Total Immersion |          |
|------------------------------------|------------------|---------------------|-------------------------------------|----------|
|                                    |                  |                     | 10 minutes                          | 24 Hours |
| Plain Mortar                       | .34              | 100%                | 1.28%                               | 4.10%    |
| Concrete with „Liquid“ Waterpeller | .8               | 28 %                | —                                   | —        |

**Dosing rates**

Add 0,8 Lt of BETONAC-DM 2 per bag of cement

**Packaging**

BETONAC-DM 2 is packaged in 210 Lt drums and 20 Lt pails

**Storage/Shelf life**

1 year in original, unopened package and must be stored above 0 °C

**Directions for use**

Add BETONAC-DM 2 to concrete or mortar in the following proportions: 0.8 Lt per bag of cement.

In cement-lime mortar the above quantities should be added for each 0.03 m<sup>3</sup> of lime, in addition to the quantity added for each bag of cement. BETONAC-DM 2 may be added to the mix after all other components have been added.

The aggregate size should be from 5 to 25 mm. The mixing time of water repellent admixtures should be at least 3 minutes. Water repellent concrete should be cured during early time for 7 days at least under moisture condition

**Legal notes**

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from these of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

**LEYDE-PRODUCTS** are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 01.09.2009