

CURASIN[®]-W 1 A TP

CURASIN[®]-W 1 A WP_{REFLECTIVE}

WATER-BASED CURING COMPOUNDS

Product Description

Not only the correct composition and preparation of concrete is important, but also the after-treatment, which is one of the deciding factors with regard to quality. In case of insufficient after-treatment, the required moisture escapes too quickly, especially from the surface.

The negative results are as follows:

- insufficient development of strength
- silting and chipping of the surface
- crack formation

FACTORS EFFECTING EVAPORATION

WIND, the speed of the wind rises from 0 to 15 km/h, the water in the concrete evaporates 3 times faster, again if the change is from 0 to 40 km/h, the rate of evaporation increases 6 times.

TEMPERATURE, if the air temperature rises from 10 °C to 25 °C, the water in the concrete evaporates 3 times as fast, again if the temperature rises from 10 °C to 30 °C, the speed of evaporation increases 5 times.

HUMIDITY, if the relative humidity drops from 90 % to 50 %, the rate of evaporation increases by approx. 400 %; if it drops to 40 %, the rate of evaporation increases by approx. 500 %.

Advantages

- Prevents shrinkage cracks and other damage to the concrete caused by a rapid drying out.
- Saves from the trouble of keeping the concrete wet during the first few weeks after fabrication.
- Economical - low water consumption, low labour cost.
- Disintegrates after approx. 1 month so that the surfaces can be painted.

Technical Data

	CURASIN –W 1 A TP	CURASIN –W 1 A WP
STANDARD COMPLIANCE	ASTM C 309, TYPE I, CLASS A	ASTM C 309, TYPE II, CLASS A
Specific Gravity @40°C	0.9902 gm/ml	0.9912 gm/ml
Min. application temp.	+4 °C	+4 °C
Appearance / Color	White	White
Coverage	4 ~ 5 m ² / kg	4 ~ 5 m ² / kg
Packaging	210 Kg	210 Kg

LeycoChem LEYDE-Iraq

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151
 Email: sales.leycochem.iraq@leyde.com
www.leyde.com

LeycoChem LEYDE GmbH Germany

Industriestrasse 155 Tel.:+49(0)2236-96600-0
 P.O. Box 501627 Fax:+49(0)2236-96600-10
 D-50999 Köln/Cologne Email: leycochem@leyde.com

Product Data Sheet

Product No: 02.017

Characteristics

CURASIN-W/1A protects fresh concrete against untimely drying out - against a „burning“ of fresh concrete surfaces whose are exposed to strong solar radiation.

It also protects against erosion by rain, tap water, and aggressive atmospheric conditions.

Storage/Shelf life

Store tightly sealed in a cool and dry place. Protect from direct sunlight. Storage temperature must not exceed + 48 °C.

Application

Method of Application

Before CURASIN-W/1A is applied, the contents of the container should be thoroughly stirred or mixed by shaking. CURASIN-W/1A should be applied by a spraying unit from approx. 1 m so that a uniform and even coating is guaranteed.

It should be observed that before painting or plastering, the surfaces should be treated with a stiff brush in order to remove all traces of the curing compound. An over dosage will increase the time factor of disintegration.

For interior surfaces which will be painted or plastered, please request a special quality of curing compound from the manufacturer.

Cleaning

Tools and equipment should be cleaned with water immediately after use.

Safety Instructions

Safety precautions

CURASIN-W/1A does not contain substances which may cause damage to concrete. The product is physiologically harmless.

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from these of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 24.10.2011