

LEYCO[®]-POX 102

SOLVENT-BASED EPOXY PRIMER AND SURFACE HARDENER

Product Description

LEYCO-POX 102 is an extremely low-viscous solvent-based epoxy primer used for deep penetration of concrete and concrete plaster.

Uses

As a clear impregnation or sealing coat for cementitious floors and wall-plaster, to provide dust-proof and easy-to-clean surfaces, subject to traffic in accordance with MIB-I, and surfaces according to penetration of chemicals, grease, oil, solvents, in workshops, petrol stations, filling plants, underground garages, parking areas, hangars etc.

Advantages

- Very low viscosity
- High capillary activity-deep penetration.
- To be used on old and fresh concrete.
- Does not stop breathing of concrete and plaster.
- Stops capillary activity in concrete, mortar and cement plaster.
- Can be used at low and high temperatures
- High chemical resistance.

Technical Data

Mixing ratio (by weight)

A:B =100:18

Density

0,93 g/cm³

Flash point

>21 °C

Pot life

10 °C 20 hrs

20 °C 10 hrs

30 °C 5 hrs

Repaint able

4-48 hrs

Final curing

7 after Days

Solid contents

55 %

Storage / Shelf life

In cool and dry store, the shelf life is 1 year in original sealed container

البيكو كيم العراق
LEYCOCHEM LEYDE Iraq

LEYCOCHEM-IRAQ Baghdad

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151

Email: sales.leycochem.iraq@leyde.com

Email: admin.leycochem.iraq@leyde.com

www.leyde.com

LeycoChem LEYDE GmbH Germany

Industriestrasse 155

P.O. Box 501627

D-50999 Köln/Cologne

Tel.:+49(0)2236-96600-0

Fax:+49(0)2236-96600-10

Email: leycochem@leyde.com

Product Data Sheet

Product No: 30.102

Application

Mixing

The entire contents of the hardener (comp. B) should be poured into the resin (comp. A) and the two components thoroughly mixed. Reduce wastage by not making up more than can comfortably be applied within the pot life.

Method of application

Apply by roller or airless sprayer on clean, sound surface which is free from grease, oil or any contamination. Apply in 1-3 stages "wet in wet" with intervals of approx. 15 min. to achieve maximum penetration into surface.

Consumption

150-200g / m² / per layer

Cleaning

Tools and equipment should be cleaned with LEYCO-Thinner/Cleaner immediately after use.

Important Note

a) Humidity of air shall not exceed 85 %.

b) The material contains solvents.

Make sure that closed rooms are well ventilated.

Safety Instructions

Safety precautions

Gloves, barrier cream or protective clothing should be used. Prolonged skin contact may cause irritation. If accidentally splashed into eyes, flush with plenty of water and seek medical attention immediately. For further details refer to the MSDS which is available under www.leyde.com

Note

Flammable

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 01.09.2009