

Product Data Sheet

Product No: 30.103/S

Application

Surface Conditions

The substrate must be firm, clean, dry and free from all contamination. All loose particles and excess laitance should be removed by mechanical or chemical methods.

Mixing

The entire contents of the hardener (comp. B) should be poured into the resin (comp. A) and the two components thoroughly mixed. Reduce wastage by not making up more material than can be comfortably applied within the pot life.

Method of application

For injection with LEYCO-POX 103/S, see separate leaflet with the relevant technical instructions.

For production of filling compounds and repair mortars please request formulations and mixing instructions from manufacturer. Can be applied with brush roller or airless spray.

Cleaning

Tools and equipment should be cleaned with LEYCO-CLEANER immediately after use.

Safety Instructions

Safety precautions

Gloves, barrier cream or protective clothing should be used. Prolonged skin contact may cause irritation. If accidentally splashed into eyes, flush with plenty of water and seek medical attention immediately.

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 01.09.2009