

LEYCO[®]-POX104

EPOXY RESIN PRIMER + ADHESIVE PRIMER

Product Description

When cured, LEYCO[®]-POX104 forms a matt surface with excellent adhesion to almost all smooth surfaces; as primer coat for the application of epoxy resin coating. LEYCO[®]-POX104 is waterproof and resistant to sewage, seawater, diluted acids, lyes, heating oil, motor oil and gasoline. It can accept temperatures from -30 °C to + 90 °C.

Uses

LEYCO[®]-POX104 is a 2-component epoxy resin dispersion consisting of a special pigmented hardener and liquid epoxy resin. LEYCO[®]-POX104 is used as a special primer coat for absorbent and non-absorbent horizontal and vertical surfaces where an ultimate adhesive strength for subsequent coatings based on epoxy resin is required. LEYCO[®]-POX104 is applied on new and existing coatings and areas where no mechanical key (or sandblasting) is possible, and where high bond strength is required. LEYCO[®]-POX104 is applied as primer on old existing epoxy coatings, tiles, smooth concrete, rendering, steel prior to application of LEYCO[®]-POX109, LEYCO[®]-POX121, LEYCO[®]-POX122, LEYCO[®]-POX124, LEYCO[®]-POX126, LEYCO[®]-POX127.

Advantages

- Solvent-free
- No fire hazard
- No special ventilation required

Technical Data

Mixing ratio (by weight) A:B =	10:3
Viscosity DIN 4 mm	95 sec.
Density	3/1.5 g/cm ³ (at 23 °C)
Pot life	90 min. (at 23 °C) 60 min. (at 30 °C)
Minimum curing temp.	12 °C
Tack free	4 hours (at 23 °C)
Over coating	4-24 hours (at 23 °C)
Accessible	12 hours (at 23 °C)
Final strength	7 days (at 23 °C)

Adhesive strength on concrete: greater than the tensile strength of the concrete.

Storage/Shelf life

12 months in originally sealed containers, in a cool, frost-free, dry store.

Application

Surface Conditions

The substrate must be clean, firm and free from laitance. The temperature of the substrate should be min. 3 °C and the relative humidity must not exceed 85 % at 23 °C. After application, LEYCO[®]-POX104 should be protected from moisture for 5 - 6 hours (at 23 °C and 50 % relative humidity).

LEYCOCHEM-IRAQ Baghdad

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151

Email: sales.leycochem.iraq@leyde.com

Email: admin.leycochem.iraq@leyde.com

www.leyde.com

LeycoChem LEYDE GmbH Germany

Industriestrasse 155

P.O. Box 501627

D-50999 Köln/Cologne

Tel.:+49(0)2236-96600-0

Fax:+49(0)2236-96600-10

Email: leycochem@leyde.com

Product Data Sheet

Product No: 30.104

Mixing

Pour entire contents of comp. B into comp. A and mix thoroughly Reduce wastage by not making up more than can be applied within pot life.

Method of application

Apply with brush roller or airless sprayer.

Example of use

Prepare surface as a.m. Apply LEYCO®-POX104, 200-250 g/m². After 1-2 days, apply top coat based on solvent-free epoxy resin (e.g. LEYCO®-POX109, LEYCO®-POX121, LEYCO®-POX122, LEYCO®-POX124, LEYCO®-POX126, LEYCO®-POX127 and LEYCO®-POX128).

Cleaning

With water, immediately after use.

Safety Instructions

Safety precautions

Gloves, barrier cream or protective clothing should be used. Prolonged skin contact may cause irritation. If accidentally splashed into eyes, flush with plenty of water and seek medical attention immediately.

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 01.09.2009