

LEYCO®-TEKT3

LOW VISCOSITY PRIMER, BINDER AND WATERPROOFING ADMIXTURE WITH A BITUMEN EMULSION BASE

Description

LEYCO-TEKT 3 is a multi-use primer and binder for mineral aggregates and sand

Advantages

- 1 component
- excellent adhesion to bitumen and mineral substrates
- cures fast, fills pores binds mineral aggregates and dust
- as plaster mortar admixture to improve water resistance and reduce permeability
- solvent free

Technical Data

Type of binder:	bitumen
Appearance:	brown, low viscosity
Application temperature:	+5 up to +55°C
Solid content (DIN 53215):	approx. 35%
Softening point of the solid material (DIN 52011):	approx. 55°C
Density (DIN 52004):	approx. 1,00 g/cm ³

Storage /Shelf life

When stored in sealed original packing under shed, not exposed to direct sun and not less than +5C°, shelf life is 1 year.

Application

Surface preparation

The substrate to be treated must be clean, sound and free from oil and grease. Remove any edges and ridges. Large pores and honeycombs must be filled with a mortar mix, consisting of 1 part LEYCO-TEKT 3 and 5 to 8 parts of sand. Before application the substrate must dry or slightly damp.

Use as primer

Ready-to-use with a bitumen emulsion base and high penetration in mineral substrate



Application

By brush or suitable spray equipment. The ambient temperature must be min. +5 C° and max. 55 C°. The consumption is approximately 0,2 to 0,3 kg m² depending on substrate.

Use as Binder for Mortar, Sand and Plastermixes:

LEYCO-TEKT 3 is an ideal binder to produce cold bituminous repair mortar and levelling compound.

Mixing ratio suggestion:

- For repair of joints and broken edges use 1 part b.w. of LEYCO-TEKT 3 and 3 parts b.w. of sand.
- As binder for bituminous levelling mortar and screed use 1 part b.w. of LEYCO-TEKT 3 and up to 8 to 10 parts of sand, depending on load requirement.
- To produce water proofing plaster, add to the volume of cement mortar approx. 10 % of LEYCO-TEKT 3. Gauging water of cement mortar must be reduced in same ratio.

LeycoChem LEYDE-Iraq

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151
Email: sales.leycochem.iraq@leyde.com
www.leyde.com

LeycoChem LEYDE GmbH Germany

Industriestrasse 155 Tel.:+49(0)2236-96600-0
P.O. Box 501627 Fax:+49(0)2236-96600-10
D-50999 Köln/Cologne Email: leycochem@leyde.com

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 29.08.2011