

LEYCO®-TEKT6

A HIGHLY PENETRATIVE, GENERAL PURPOSE, BITUMEN PRIMER AND TOP COATING

Uses

LEYCO-TEKT 6 is used as primer for priming surfaces prior to application of bituminous materials and as top coat on roofs and floors, cementitious screeds/renders, bitumen felt, mastic asphalt, weathered corrugated iron and steel. It is recommended for use with the LEYCOPLAST range of bituminous coating, flashing tapes or mastics.

Advantages

- fulfils the requirements of AIB DS 835.9101 (German Railway Standard)
- highly penetrative
- ready for use
- very good bond on bituminous and mineral substrate
- resistant to aqueous solvents, diluted acids, salts, lime, cements and similar
- fast setting
- dust proofer

Technical Data

Nature:	fluid
Kind of binder:	bitumen
Kind of solvent:	white spirit
Mass content of solvent bitumen (DIN 1996)	approx. 60 %
Drying time until dust dry (DIN 53 150)	approx 2,5 h
Flashpoint (DIN 53 213):	> 21 °C
Running out time (ISO 2431):	> 70 s
Heat resistance at 70 °C (AIB):	no draining
Water impermeability (0,2 bar, 8 h) (AIB):	tight
Density (DIN 52 004):	approx. 0,9 g/cm ³
Danger warning:	R 10 flammable
Class or risk in accordance with VbF:	A II

Storage /Shelf life

In sealed original packages for at least 12 months, in dry and cool condition.
Protect from direct sun.

Application

Preparation

All surfaces must be structurally sound, clean, dry and free from surface contaminants such as grease, rust and dirt. If necessary, remove any organic growth i.e. moss or lichen, with a fungicidal wash. On bare metal a rust inhibiting product, such as red oxide or zinc phosphate should be applied and allowed to harden.

LeycoChem LEYDE-Iraq

Tel.: 0750-4344200, Tel.:0770-8748222, Tel.:0781-3802151
Email: sales.leycochem.iraq@leyde.com
www.leyde.com

LeycoChem LEYDE GmbH Germany

Industriestrasse 155 Tel.:+49(0)2236-96600-0
P.O. Box 501627 Fax:+49(0)2236-96600-10
D-50999 Köln/Cologne Email: leycochem@leyde.com

Product Data Sheet

Application

Stir before use! Apply by brush, roll or spray. Using a brush, scrub LEYCO-TEKT 6 into the surface. Ensure that always thin coats are applied and that there is no pooling. Alternatively, spray thinly and evenly. Priming should extend at least 75 mm beyond the area to be waterproofed. Leave to dry 1-2 hours before continuing with further work.

With fibre cement or dry rag bituminous felts, apply generously to saturate the surface.

Material consumption:

For each working step approx. 0, 5 l/m² LEYCO-TEKT 6 is required.

Packing:

5 l -, 10 l - and 30 l metal cans and 200 lt. metal drum

Safe Handling Precautions:

Flammability: Keep away from sources of ignition, keep containers closed when not in use and DO NOT SMOKE!

Skin Contact: Avoid skin contact by careful working and use barrier crème, wear gloves and protective cloth. Remove skin contact immediately with a proprietary hand cleaner and wash with soap.

Eye contact: In the event of accidental contact, wash eyes 15 min with water and obtain medical assistance.

Inhalation: Contains solvents. Stand upwind of the work and avoid inhalation. In closed rooms use strong ventilation with fresh air!

Legal notes

Whilst information and/or specification contained herein is to the best of our knowledge true and accurate, and is based on many years experience, we cannot accept any liability either directly or indirectly arising from the use of our products, whether or not in accordance with any advice, specification or recommendation given by us, as we have no direct or continuous control over how or where our products are applied.

LEYDE-PRODUCTS are guaranteed against defective materials and manufacture and are sold subject to its standard terms and conditions of sale. 29.08.2011